Ash Collection and Utilization, 1966-1976

History of the Coal Combustion Byproduct Survey

	Ash Utilized in Millions of Tons				Ash Produced in Millions of Tons				Percentage of Ash Utilization			
Year	Fly Ash	Bottom Ash	Boiler Slag	FGD Material *	Fly Ash	Bottom Ash	Boiler Slag	FGD Material*	Fly Ash	Bottom Ash	Boiler Slag	FGD Material*
1966	1.4	1.7			17.1	8.1			8.187	20.988	ERR	ERR
1967	1.4	2.3			18.4	9.1			7.609	25.275	ERR	ERR
1968	1.9	1.8	1.5		19.8	7.3	2.6		9.596	24.658	57.692	ERR
1969	1.9	2	1		21.1	7.6	2.9		9.005	26.316	34.483	ERR
1970	2.2	1.8	1.1		26.5	9.9	2.8		8.302	18.182	39.286	ERR
1971	3.3	1.6	3.7		27.8	10.1	5		11.871	15.842	74.000	ERR
1972	3.6	2.6	1.3		31.8	10.7	3.8		11.321	24.299	34.211	ERR
1973	3.9	2.3	1.8		34.6	10.7	4		11.272	21.495	45.000	ERR
1974	3.4	2.9	2.4		40.4	14.3	4.8		8.416	20.280	50.000	ERR
1975	4.5	3.5	1.8		42.3	13.1	4.6		10.638	26.718	39.130	ERR
1976	5.7	4.5	2.2		42.8	14.3	4.8		13.318	31.469	45.833	ERR