Ash Production Ash Utilization — 1985

	(Million Tons)
I. ANNUAL COAL CONSUMPTION	656.98
II. TOTAL ASH PRODUCED	65.11
III. ASH UTILIZED	17.87

	FLY ASH	BOTTOM ASH	BOILER SLAG
1. EXTERNAL UTILIZATION			
a. Cement and concrete products	5.10	.44	.12
b. Structural fills	.38	.35	.10
c. Road base	.38	.27	.14
d. Filler in asphalt mix	.05	.01	.02
e. Snow and ice control	.004	.58	.40
f. Blasting grit and roofing granules	.002	.03	1.38
g. Grouting	.29	-0-	-0-
h. Coal and mining applications	.83	.19	-0-
i. Miscellaneous	.88	.05	.07
TOTAL EXTERNAL UTILIZATION	**7.91**	**1.92**	**2.23**
2. INTERNAL UTILIZATION			
a. Cement and concrete products	.005	-0-	-0-
b. Structural fills	1.13	1.19	.08
c. Road base	.12	.31	.008
d. Miscellaneous	2.23	.68	.07
TOTAL INTERNAL UTILIZATION	**3.48**	**2.18**	**.158**
3. TOTAL ASH UTILIZED	**11.39**	**4.10**	**2.38**
4. ASH REMOVED TO DISPOSAL AREA AT COMPANY EXPENSE WITH NO UTILIZATION	36.92	9.05	1.27
5. TOTAL ASH PRODUCED	**48.31**	**13.15**	**3.65**

Comparative Results

	*1966	1980	1981	1982	1983	1984	1985
Ash Produced							
Fly Ash	17.1	48.31	50.26	47.91	47.15	51.32	48.31
Bottom Ash	8.1	14.45	12.87	13.13	12.73	13.62	13.15
Boiler Slag	-0-	3.64	5.18	4.37	3.94	4.21	3.65
TOTAL ASH PRODUCED	**25.2**	**66.40**	**68.31**	**65.41**	**63.82**	**69.15**	**65.11**
Ash Utilized							
Fly Ash	1.4	6.42	9.41	7.95	7.52	10.43	11.39
Bottom Ash	1.7	4.26	4.07	3.63	2.76	2.96	4.10
Boiler Slag	-0-	1.75	2.93	1.97	2.53	2.65	2.38
TOTAL ASH UTILIZED	**3.1**	**12.43**	**16.41**	**13.55**	**12.81**	**16.04**	**17.87**
Percent of Ash Utilized							
% Fly Ash	7.9	13.3	19.0	16.6	15.9	20.3	23.5
% Bottom Ash	21.0	29.5	32.0	27.6	21.6	21.7	31.1
% Boiler Slag	-0-	48.1	57.0	45.1	64.2	62.9	65.2
PERCENT OF TOTAL ASH UTILIZED	**12.1**	**18.7**	**24.0**	**20.7**	**20.0**	**23.1**	**27.4**

*First year that data was taken

1967-1979 data omitted from tabulation because of space limitation.

Compiled by the American Coal Ash Association, Inc. • 1819 H Street, N.W., Suite 510 • Washington, D.C. 20006