American Coal Ash Association (ACAA)
1997 Coal Combustion Product (CCP)
Production and Use (Short Tons)

Total CCPs - Category I (Dry) & II (Ponded)	Fly Ash	Bottom Ash	Boiler Slag	FGD Material
CCP Production	60,264,791	16,904,663	2,741,614	25,163,394
Subtotal -- Fly Ash, Bottom Ash, and Boiler Slag			79,911,068	
Total All CCPs				105,074,462
CCP Use				
Cement/Concrete/Grout	9,421,903	604,705	10,755	202,423
Flowable Fill	386,158	15,260	0	0
Structural Fills	2,877,535	1,384,327	84,669	91
Road Base/Subbase	1,417,600	1,286,585	792	17,797
Mineral Filler	285,580	130,888	108,796	0
Snow and Ice Control	0	723,615	56,057	0
Blasting Grit/Roofing Granules	0	159,749	2,288,581	0
Mining Applications	1,413,567	162,638	0	104,690
Wallboard	0	0	0	1,603,762
Waste Stabilization/Solidification	3,117,947	206,368	0	15,428
Agriculture	34,571	8,197	0	55,644
Miscellaneous/Other	362,501	414,572	29,200	183,527
Total Use	19,317,362	5,096,905	2,578,851	2,183,363
Subtotal -- Fly Ash, Bottom Ash, and Boiler Slag			26,993,119	
Total All CCPs				29,176,482
Individual Use Percentage	32.1%	30.2%	94.1%	8.7%
Cumulative Use Percentage	32.1%	31.6%	33.8%	27.8%

For metric equivalents, multiply tabular values by 0.9078

American Coal Ash Association
2760 Eisenhower Avenue, Suite 304 ⁘ Alexandria, VA 22314-4569 ⁘ USA
Phone: 703-317-2400 ⁘ Fax: 703-317-2409 ⁘ Internet: http://www.ACAA-USA.org